www.flexura-floors.be

Technical sheet

0.6 MM ON 8 MM HDF WITH 2 MM CORK BACKING - 1500 X 190 X 10,6 MM

F EXURA OODEN FLOORS



BOARD STRUCTURE

FINISH

Lacgered (Sherman Williams)

TOP LAYER 0,6 mm European oak (nominal)

MIDDLE LAYER

8 mm high density fibre board (HDF) Swelling max. 15%

BOTTOM LAYER 2 mm cork backing



Average density of the board is 870 kg per m³, on surface up to 1200 kg per m³. The bonding agent between top layer veneer and the supporting middle layer HDF board is a E1 class urea-formaldehyde glue especially developed for form pressing and veneering.

LACOUERING SYSTEM

Lacquering system is designed to achieve the highest class of new European norm EN14354 for wood veneer floors especially with respect to abrasion resistance (class 32). All edges are sealed with waterproof protection on V-Groove.

UNDERFLOOR HEATING

Floor can be used on underfloor heating with a maximum temperature of 27 degrees Celcius.

REACTION TO FIRE

Goods are tested at wood.be in Belgium again norm EN13501 which has a CFL/S1 certificate.

OVERALL SIZE: 1500 x 190 x 10,6 mm

